

PRODUCT DATA SHEET

Spray adhesive GLUKON prime

Pressure vessel 13 kg

Item no. 1429



Status: 02.08.2026 | 01:29



Designation	Spray adhesive GLUKON prime Pressure vessel 13 kg
Description	Adhesive and contact adhesive for the assembly of filler profiles made of composite, rigid PVC or metal on various substrates. Web spray in mobile pressure tanks for quick and easy application of the adhesive with the spray gun. Very high initial tack, short flash-off time of 1 - 5 minutes, open time of 12 hours. Also suitable for a variety of other materials and applications.
Product area	Interior finishing
Product category	Profile glue
Revision	After setting and pressing on the filler profiles, the filling process can begin immediately.
Application Areas	Fixation of Protektor composite, rigid PVC and aluminum profiles on a wide variety of substrates, especially gypsum plasterboard and other board materials. As a contact adhesive - applied on both sides - also suitable for the bonding of other materials such as PE foils, vapor barriers, insulating materials such as EPS/XPS insulating panels, PUR/PIR rigid foam, acoustic foam, etc. As a pressure-sensitive adhesive - applied on one side - the spray adhesive GLUKON prime improves the adhesion of all common acrylate, butyl, bitumen and rubber adhesive tapes on absorbent substrates and serves as a quick fixation when installing geotextiles, facade membranes, underlay membranes, vapor barriers, underlays railways, etc. Materials and substrates containing plasticizers such as soft PVC, artificial leather, etc. are not suitable for bonding with GLUKON prime!
Appearance	Transparent-yellowish
Materialbase	Solvent-based spray adhesive made from styrene-butadiene rubber. Free from dichloromethane and toluene. Hardly inflammable (building material class B1 according to DIN 4102-1). GLUKON prime has been tested for harmful substances. Among other things, it meets the requirements for VOC emissions on the basis of the emissions test, VOC and SVOC according to the testing and evaluation scheme of the committee for health-related evaluation of building products (AgBB scheme). Meets the requirements of the French VOC regulation class A+.
Underground	The substrate must be dry and free of dust and grease before bonding. Loose and not firmly adhering residues and dirt such as concrete and cement veils, paint residues, etc. must be removed. Adjacent surfaces must be covered. Suitable substrates for use as a pressure-sensitive or contact adhesive are, in particular, gypsum plasterboard, fiber cement board, wood fiber board. But also masonry, plaster, concrete, aerated concrete, cement, tiles, rubber, hard foam, Foam, aluminium, sheet metal, bitumen sheeting, cork, leather, wood, MDF, chipboard/blockboard, OSB, mineral fiber insulating materials and most Hard plastics, EPS/XPS, PIR/PUR and much more.

PRODUCT DATA SHEET

Spray adhesive GLUKON prime

Pressure vessel 13 kg

Item no. 1429



Treatment	Shake/roll the container thoroughly for at least 1 minute before using it for the first time or after a long period of inactivity. Connect the hose and gun to the tank and slowly open the tank valve (check the system for leaks). Apply spray adhesive GLUKON prime evenly and quickly to one side of the substrate (avoid puddles of adhesive). To do this, hold the spray gun at a distance of approx. 10 cm from the surface (rule of thumb: for correct application: spray jet width = spray jet distance). After the drying time of approx. 1 minute (at 25°C) to 5 minutes (at -10°C) apply the spatula profile and press down immediately with a suitable roller tool. A double application is recommended for highly absorbent substrates. Applying adhesive to both sides (on the substrate and on the inside of the profile) increases adhesion even further. Important note: Movement joint profiles must also be mechanically fastened with clamps. Lock the spray gun after use, NEVER close the container valve (only when changing the container or transporting to the construction site).
Consumption	Coverage 13 kg pressure tank as adhesion primer (single application): Approx. 130-170 m ² , approx. 2250-3000 linear meters (5 cm spray width). Consumption depends heavily on the absorbency of the substrate.
Tool Cleaning	Clean tools such as pressure rollers or surfaces soiled with adhesive with GLUKON Citrus Cleaner and a lint-free cloth.
Treatment Temperature	Not below -10°C (air/material temperature). Make sure the gallons are at the right temperature (at least 15 °C).
Overplastering Ability	When setting paper-coated composite profiles with PROTEKTOR profile adhesive, the paper wings perforated in the edge area must be pressed separately onto the substrate that is fully coated with profile adhesive.
Storage life	At temperatures between +10 °C and +50 °C. The container is under pressure. Protect containers from direct sunlight and sources of heat. Storage only in well-ventilated rooms. Do not store on the cold concrete floor. Avoid damaging the containers or the entry of foreign objects. The containers must not be refilled! Transport containers upright and secure against shifting/falling over. Close container valve during transport. Protect containers from rain. Handle containers with care. Don't throw or drop. Storage only in well-ventilated rooms. Containers that show external damage such as dents on the housing or valve damage must be disposed of properly. Do not insert any objects into the spray head! Please also note the safety data sheet for pressure vessels (item 7 and item 14). Can be stored for at least 18 months when stored under the recommended conditions.
Disposal	In accordance with official regulations.
Security Advice	Good ventilation of the workplace/construction site must be guaranteed or ensured by suitable technical measures. When working with GLUKON prime spray adhesive, personal protective equipment should be used (gloves, protective goggles). The information in the safety data sheet must be observed!
Annotation	When setting paper-coated composite profiles with PROTEKTOR profile adhesive, the paper wings perforated in the edge area must be pressed separately onto the substrate that is fully coated with profile adhesive.
Customs tariff number	35069900
Opened label	Purchase only possible as full packaging units.

Item number	Length (cm)	Packaging unit
118503	48.00	1 PCE / 12 BOX

This product data sheet corresponds to the current state of development of our products and loses its validity upon publication of a new edition. Make sure you are using the latest edition of this information. Warranty and liability are based on delivery according to our general Terms and conditions. Please observe the application assembly and storage guidelines.

All statements without guarantee. Reserve technical changes. Product illustrations may differ from the delivery product. Tender specifications, installation instructions and performance declarations (if required by law) can be found on our homepage. Please respect the environment for a proper disposal!